

Bona Wood Floor Refresher

Technical data sheet

Bona Wood Floor Refresher is a ready-to-use waterborne maintenance coating for most finished and pre-finished wooden floors in both commercial and domestic areas. It revives a scratched and dull surface giving a newly finished look and continuing protection against wear.

- Specifically designed for finished wooden floors.
- Based on polyurethane = superb protective qualities.
- Contains no waxes.
- Allows for future applications of professional finish.
- Meets EN 14904:2006 and DIN 18032:2 for slip resistance.

Technical data

Binding agent:	Polyurethane
Dilution:	Do not dilute - the product is ready-to-use
Drying time:	Approx.. 2 hours (20°C/60% RH)
Application tools:	Bona Microfibre Applicator Pad
Coverage:	Ca. 30-50 m ² /litre
Safety:	Unclassified
Shelf life:	2 years, from date of production, in unopened original container
Storage/Transport:	The temperature must not fall below +5°C or exceed +25°C during storage and transport.
Disposal:	Wastes and emptied containers should be handled in accordance with local regulations.
Pack size:	12 x 1 litres (32 boxes per pallet)


Preparations

Remove loose dirt and grit from your floor. Clean floor thoroughly with Bona Wood Floor Cleaner. Repeat to ensure that dirt will not be trapped in the coating. Make sure the floor is completely dry before applying Bona Wood Floor Refresher. Do not use over any floor that has been waxed or oiled. Wax and oil residues will prevent the proper adhesion of Bona Wood Floor Refresher to the floor. **Always test floors for appearance and adhesion in an inconspicuous area before use.**

Application



1. Rock container back & forth several times before opening. Apply Bona Wood Floor Refresher with the Bona Microfiber applicator pad. Prepare the applicator pad by slightly dampening it with water. Apply in a 3-4 cm wide wavy line on the floor. Work on a small section at a time, about 3 m².



2. Spread the product over entire small section making sure all wood is covered. The application should be done at approx. 30-50 m² per litre. For best results, apply a thin consistent coat. Keep airborne dust and airflow to a minimum while floor is wet.


Floor Care



Bona Wood Floor Refresher

Technical data sheet

Floor Care



3. Smooth out, going with the grain of the wood. Continue the process until the entire floor is coated. Allow to dry a minimum of 2 hours before walking on coated floors. If needed, a second coat may be applied after this time. Always coat the entire floor to ensure an even appearance and sheen.

Note: Avoid heavy traffic and replacement of furniture and rugs for 24 hours after the final coat. Clean tools with soap and water.

Maintenance

Damp-cleaning of the floor may be resumed after one week. To keep the floor in good health use the Bona Floor Cleaning System regularly. Do not use strongly alkaline cleaning agents as they may damage the floor. For floors in homes, one or two applications of Refresher a year is usually enough to protect the floor. Inspect the floor occasionally to ensure that the maintenance schedule is reflecting the level of wear.

Bona[®]